# **PRODUCT SPECIFICATION SHEET**

Customer Satisfaction Membrane

### CSM RO MEMBRANE, The approved *Reverse Osmosis Membrane* in the world.

®

## **RE2540-SR**

High rejection RO membrane element for sea water and high salinity well water

Product Specifications	Permeate Flow rate :	500 GPD (1.9 m³/day)
	Stabilized Salt Rejection :	99.6 %
	Effective Membrane Area :	24 ft <sup>2</sup> (2.2 m <sup>2</sup> )
	32,000 mg/L NaCl solution at 800 ps	a taken after 30 minutes of operation based on the following conditions; ig (5.5 MPa) applied pressure, 8 % recovery, 77 °F (25 °C) and pH 6.5-7.0. polyethylene bag containing 1.0 % SBS (Sodium bisulfite) solution and packaged individual
Product Description	Membrane Type :	Thin-film Composite
	Membrane Material :	PA (Polyamide)
	Membrane Surface Charge :	Negative
	Element Configuration :	Spiral-Wound, Tape wrapping
Product Dimensions	A = 40 inch (1,016 mm)	
	B = 2.5 inch (64 mm)	
	C = 0.75 inch (19.1 m	nm)
	U-cup seal	Find con permeate channel
	(Brine seal) FRI	P wrapping End cap
		CSM (element outer diameter) B (element outer
	1	(element length)
		vould be supplied for each membrane element. fit nominal 2.5-inch (64 mm) I.D. pressure vessel.

# PRODUCT SPECIFICATION SHEET

### **Customer Satisfaction Membrane**

#### Conditions for Handling CSM in general

R

- Customers must keep the element boxes dry at room temperature to prevent them from freezing and damages from heat. If the polyethylene bag is broken, a new protective solution has to be added to the RO membrane element and the element has to be repackaged air-tight to prevent from biological growth.
- Keep elements moist at all times after initial wetting
- Permeate water obtained from first hour of operation should be discarded in order to flush the protective solution in the elements.
- CSM elements should be immersed in a protective solution during storage, shipping or system shutdowns to prevent biological growth and freeze damage. The standard storage solution contains one (1) weight percent sodium bisulfite or sodium metabisulfite (food grade). For short term storage of one week, one (1) weight percent sodium metabisulfite solution is adequate for inhibiting biological growth.
- The customer is fully responsible for the effects of incompatible chemicals on elements. Their use will void the element limited warranty.

#### **Application Data**

#### **Operating Limits**

 Max. Pressure drop / Element 15 psi (0.1 MPa) • Max. Pressure drop / 240" vessel 60 psi (0.41 Mpa) Max. Operating pressure 1,200 psi (8.27 MPa) Max. Feed flow rate 6 gpm (1.36 m<sup>3</sup>/hr) Min. Concentrate flow rate 1 gpm (0.23 m<sup>3</sup>/hr) Max. Operating temperature 113 °F (45 °C) 3.0 ~ 10.0 Operating pH range CIP pH range 2.0 ~ 11.0 1.0 NTU Max. Turbidity Max. SDI (15 min) 5.0 • Chlorine concentration < 0.1 mg/L

#### Design Guideline for Various Water Source

- • Waste water (SDI < 5)</td>
   8 ~ 12 gfd

   • Waste water pretreated by UF (SDI < 3)</td>
   10 ~ 14 gfd

   • Seawater, open intake (SDI < 5)</td>
   7 ~ 10 gfd

   • High salinity well water (SDI < 3)</td>
   8 ~ 12 gfd

   • Surface water (SDI < 5)</td>
   12 ~ 16 gfd

   • Surface water (SDI < 3)</td>
   13 ~ 17 qfd
- Surface water (SDI < 3)</th>
   13 ~ 17 gid

   Well water (SDI < 3)</td>
   13 ~ 17 gid
- RO/UF permeate (SDI < 1) 21 ~ 30 gfd

#### Saturation Limits for Salts

CaSO <sub>4</sub>	230 % saturation
<ul> <li>SrSO<sub>4</sub></li> </ul>	800 % saturation
• BaSO <sub>4</sub>	6,000 % saturation
<ul> <li>SiO<sub>2</sub></li> </ul>	100 % saturation

Above values are saturation limit at the tail end of the membrane elements for each sparingly soluble salts with proper scale inhibitor.

#### CaCO<sub>3</sub> Scaling potential limits as LSI or SDSI

- Without scale inhibitor <-0.2
- LSI (SDSI) with SHMP < +0.5
- LSI (SDSI) with special inhibitor<sup>1</sup> < +1.5
- SDSI with any inhibitor < +0.5

1. Special inhibitor means one of approved organic inhibitors. It should be approved from real plant for more than three years.

For more information about CSM membranes; 12<sup>th</sup> Floor ASPO Bd., 254-8 Kongduk-Dong, Mapo-Gu, SEOUL 121-710, KOREA TEL +82-2-3279-7514, +82-2-3279-7367 FAX +82-2-3279-7088 Email <u>csm@wjchemical.co.kr</u> Website <u>http://www.csmfilter.com</u>