

# NE8040-40

High productivity NF element with low monovalent ion rejection

# CSM<sup>®</sup>

- High Mono/Multivalent Ion Selectivity
- High Hardness Rejection
- Low Energy Consumption



Food



Municipal



Water Reuse

## SPECIFICATIONS


### General Features

<b>Permeate Flow Rate</b>	12,000 GPD (45.4 m <sup>3</sup> /day)
<b>MgSO<sub>4</sub> Rejection</b>	99.0% (Minimum 98.0%)
<b>NaCl Rejection</b>	20 – 40%
<b>Effective Membrane Area</b>	400 ft <sup>2</sup> (37.2 m <sup>2</sup> )
<b>Membrane Type</b>	Thin-Film Composite
<b>Membrane Material</b>	Polyamide (PA)
<b>Element Configuration</b>	Spiral-Wound, FRP Wrapping

**Test Conditions:** 2,000 mg/L MgSO<sub>4</sub> or NaCl solution at 75 psig (0.52 MPa) applied pressure; 15% recovery; 77°F(25°C); pH 6.5–7.0; Permeate flow rate for each element may vary +25 / -25%.

### Dimensions and Weight

Model Name	A	B	C	Weight	Part Number	
					Inter-Connector	Brine Seal
NE8040-40	40.0 inch (1,016 mm)	7.9 inch (200 mm)	1.12 inch (28.5 mm)	15kg	SWA01049	SWA01043



1. Each membrane element supplied with one interconnector (coupler) and four O-rings.
2. All NE8040 elements fit nominal 8.0 inch (203.2 mm) I.D. pressure vessels.

#### Toray Advanced Materials Korea Inc.

For more information on our products, company and regional contacts, please visit our website at [www.csmfilter.com](http://www.csmfilter.com).  
Product Specification Sheet / Model NE8040-40

V.2.1 (22)

# NE8040-40



High productivity NF element with low monovalent ion rejection

## APPLICATION DATA

### Operating Limits

<b>Max. Pressure Drop / Element</b>	15 psi (0.10 MPa)
<b>Max. Pressure Drop / 240" Vessel</b>	60 psi (0.41 MPa)
<b>Max. Operating Pressure</b>	600 psi (4.14 MPa)
<b>Max. Feed Flow Rate</b>	75 gpm (17.0 m <sup>3</sup> /hr)
<b>Min. Concentrate Flow Rate</b>	16 gpm (3.6 m <sup>3</sup> /hr)
<b>Max. Operating Temperature</b>	113°F (45°C)
<b>Operating pH Range</b>	3.0 – 10.0
<b>CIP pH Range</b>	1.0 – 11.5
<b>Max. Turbidity</b>	1.0 NTU
<b>Max. SDI (15 min)</b>	5.0
<b>Max. Chlorine Concentration</b>	< 0.1 mg/L

## GENERAL HANDLING PROCEDURES

- Elements contained in the boxes must be kept dry at room temperature (7–32°C; 40–95°F) and should not be stored in direct sunlight.
- Permeate from the first hour of operation should be discarded.
- Stabilized salt rejection is generally achieved within 1~48 hours of continuous use.
- Keep elements moist at all times after initial wetting.
- Avoid excessive pressure and flow spikes.
- Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty.
- Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.
- The element shell is FRP(Fiber Reinforced Plastic). Be aware of glass fiber strands and use safety equipment.



Certified to  
NSF/ANSI/CAN 61

**Toray Advanced Materials Korea Inc.**

For more information on our products, company and regional contacts, please visit our website at [www.csmfilter.com](http://www.csmfilter.com).  
Product Specification Sheet / Model NE8040-40

V.2.1 (22)